

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. **(currently amended)** A method of manufacturing an optical waveguide preform, said method comprising:

providing, in a pulse, a first doping atmosphere including a first halogen-containing ~~compound gas~~ to a soot preform contained in a vessel, the first halogen-containing gas being selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂;

holding the first doping atmosphere in the vessel, and maintaining the first doping atmosphere between 1100 and 1300 °C, for a first reacting time sufficient to at least partially dope the soot preform wherein said pulse comprises a flow of the first doping atmosphere into the vessel which is interrupted prior to the first reacting time, wherein no more than 0.5 slpm of the first doping atmosphere flows out of the chamber during the first reacting time, and wherein the first doping atmosphere is pressurized to a gage pressure of at least 0.1 atm gage during the first reacting time;

evacuating at least a portion of the first doping atmosphere;

at least partially refilling the vessel with a second doping atmosphere including a second halogen-containing ~~compound gas~~, the second halogen-containing gas being selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂; and

holding the second doping atmosphere in the vessel, and maintaining the second doping atmosphere between 1100 and 1300 °C, for a second reacting time sufficient to further dope the soot preform ~~wherein the first and second halogen-containing compounds are the same~~, and wherein the second doping atmosphere is pressurized to a gage pressure of at least 0.1 atm gage during the second reacting time.

2. **(original)** The method of Claim 1 further including, following said step of holding the second doping atmosphere:

at least partially refilling the vessel with a third doping atmosphere; and

holding the third doping atmosphere in the vessel for a third reacting time sufficient to further dope the soot preform.

3. **(original)** The method of Claim 1 including:
pressurizing the first doping atmosphere about the soot preform during the first reacting time;
depressurizing the first doping atmosphere about the soot preform at the end of the first reacting time; and
pressurizing the second doping atmosphere about the soot preform during the second reacting time.

4. **(original)** The method of Claim 1 including increasing the pressure of at least one of the first doping atmosphere during the first reacting time or the second doping atmosphere during the second reacting time.

5. **(original)** The method of Claim 4 wherein the vessel is substantially completely gas-sealed throughout said step of increasing the pressure.

6. **(canceled)**

7. **(currently amended)** The method of Claim 6 1 wherein an inert gas is added to the atmosphere in the vessel during and between said steps of holding the first doping atmosphere and holding the second doping atmosphere ~~to compensate for reductions in the partial pressure of the dopant gas resulting from reaction of the dopant gas with the soot preform.~~

8. **(currently amended)** The method of Claim 6 1 wherein ~~the dopant a~~ fluorine-containing gas selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂ is added to the atmosphere in the vessel during at least one of the first and second reacting times ~~to compensate for reductions in the partial pressure of the dopant gas resulting from reaction of the dopant gas with the soot preform.~~

9. **(currently amended)** The method of Claim 6 1 further including the step of at least partially purging ~~any remaining the first doping atmosphere and any products of reaction from~~ the vessel prior to said step of at least partially refilling the vessel with the second doping atmosphere.

10. **(previously presented)** The method of Claim 1 wherein:
each of the first and second doping atmospheres includes a dopant gas;
and
additional dopant gas is added to the atmosphere in the vessel during at least one of the first and second reacting times to compensate for reductions in the partial pressure of the dopant gas resulting from reaction of the dopant gas with the soot preform.

11. **(original)** The method of Claim 1 including pressurizing an outer surface of the vessel to offset pressurization within the vessel.

12. **(original)** The method of Claim 1 including supporting a reinforcing sleeve about the vessel during at least the first and second reacting times.

13. **(original)** The method of Claim 1 including rotating the soot preform relative to the vessel and wherein the vessel is sealed.

14. **(original)** The method of Claim 1 including:
drying the soot preform prior to said step of providing the first doping atmosphere; and
sintering the soot preform following the second reacting time.

15. **(canceled)**

16. **(canceled)**

17. **(original)** The method of Claim 1 including:

pressurizing the first doping atmosphere to a first pressure during the first reacting time; and

pressurizing the second doping atmosphere to a second pressure during the second reacting time;

wherein the second pressure is different than the first pressure.

18. **(previously presented)** The method of Claim 1 including increasing a total pressure of the first doping atmosphere in the vessel during the first reacting time.

19. **(original)** The method of Claim 1 wherein the first reacting time is between about 1 and 60 minutes.

20. **(original)** The method of Claim 1 wherein the second reacting time is between about 1 and 60 minutes.

21. **(original)** The method of Claim 1 wherein the second reacting time is longer than the first reacting time.

22. **(canceled)**

23. **(original)** The method of Claim 1 including:
heating the first doping atmosphere to a first temperature during the first reacting time; and
heating the second doping atmosphere to a second temperature during the second reacting time;
wherein the second temperature is different from the first temperature.

24. **(canceled)**

25. **(cancelled)**

26. **(cancelled)**

27. (canceled)

28. (previously presented) The method of Claim 1 wherein the first and second doping atmospheres each include a fluorine-containing compound.

29. (original) The method of Claim 1 wherein the first and second doping atmospheres each include an inert gas selected from the group consisting of He, Ar, Ne, and N₂.

30. (currently amended) A method of manufacturing an optical waveguide preform, said method comprising:

providing, in a pulse, a doping atmosphere to a soot preform contained in a vessel, the doping atmosphere including a fluorine-containing gas selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂;

holding the doping atmosphere in the vessel, and maintaining the doping atmosphere between 1100 and 1300 °C, for a reacting time of between about 1 and 60 minutes to at least partially dope the soot preform wherein said pulse is interrupted prior to the first reacting time, wherein no more than 0.5 slpm of the doping atmosphere flows out of the chamber during the first reacting time, and wherein the doping atmosphere is pressurized to a gage pressure of at least 0.1 atm gage during the first reacting time; and

evacuating at least a portion of the doping atmosphere from the vessel at the end of the reacting time.

31. (currently amended) The method of Claim 30 including:

at least partially refilling the vessel with a second doping atmosphere following the reacting time, the second doping atmosphere including a fluorine-containing gas selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂; and

holding the second doping atmosphere in the vessel, and maintaining the second doping atmosphere between 1100 and 1300 °C, for a second reacting time sufficient to further dope the soot preform, and wherein the second doping

atmosphere is pressurized to a gage pressure of at least 0.1 atm gage during the second reacting time.

32. **(original)** The method of Claim 30 including:

pressurizing the doping atmosphere about the soot preform for the reacting time; and

depressurizing the doping atmosphere about the soot preform at the end of the reacting time.

33. **(original)** The method of Claim 32 wherein the vessel is substantially completely gas-sealed throughout said step of pressurizing the doping atmosphere.

34. **(currently amended)** The method of Claim 32 further including, following said step of depressurizing the doping atmosphere:

replacing at least a portion of the doping atmosphere with a second doping atmosphere about the soot preform, the second doping atmosphere being selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂; and

pressurizing the second doping atmosphere about the soot preform, and maintaining the second doping atmosphere between 1100 and 1300 °C, for a second reacting time of no more than 60 minutes to further dope the soot preform.

35. **(original)** The method of Claim 34 wherein said step of pressurizing the second doping atmosphere includes pressurizing the second doping atmosphere to a gage pressure of at least 0.1 atm.

36. **(original)** The method of Claim 35 wherein said step of pressurizing the second doping atmosphere includes pressurizing the second doping atmosphere to a gage pressure of at least 0.5 atm.

37. **(original)** The method of Claim 34 wherein the second reacting time is between about 5 and 30 minutes.

38. **(original)** The method of Claim 34 wherein said step of pressurizing the second doping atmosphere includes heating the second doping atmosphere to a temperature of between about 1125 and 1300 °C.

39. **(original)** The method of Claim 30 including pressurizing an outer surface of the vessel to offset pressurization within the vessel.

40. **(original)** The method of Claim 30 including rotating the soot preform relative to the vessel.

41. **(original)** The method of Claim 30 including:
drying the soot preform prior to said step of providing the doping atmosphere; and
sintering the soot preform following the reacting time.

42. **(canceled)**

43. **(canceled)**

44. **(currently amended)** The method of Claim ~~43~~ 30 including pressurizing the doping atmosphere to a gage pressure of at least 0.5 atm gage.

45. **(original)** The method of Claim 30 wherein the reacting time is between about 5 and 30 minutes.

46. **(canceled)**

47. **(canceled)**

48. **(original)** The method of Claim 30 wherein the doping atmosphere includes a fluorine-containing compound.

49. (canceled)

50. (canceled)

51. (currently amended) A method of manufacturing an optical waveguide preform, said method comprising:

flowing a pulse of a process gas into a vessel to provide a doping atmosphere in the vessel about a soot preform, the process gas including a doping gas selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂;

maintaining the soot preform in contact with the doping atmosphere, and maintaining the doping atmosphere between 1100 and 1300 °C, for a reacting time sufficient to at least partially dope the soot preform wherein said pulse is interrupted prior to the reacting time, wherein no more than 0.5 slpm of the doping atmosphere flows out of the chamber during the reacting time, and wherein the doping atmosphere is pressurized about the soot preform to a doping pressure greater than ambient pressure during the reacting time; and

evacuating at least a portion of the doping atmosphere from the vessel at the end of the reacting time.

52. (previously presented) The method of claim 51 further including flowing a makeup gas into the vessel during the reacting time.

53. (original) The method of claim 52 wherein the flow rate of the makeup gas is provided to at least partially offset for any pressure loss due to the doping gas reacting with the preform.

54. (canceled)

55. (cancelled)

56. (original) The method of claim 51 including flowing a second pulse of the process gas into the vessel to form a second doping atmosphere in the vessel about a

soot preform following said step of evacuating at least a portion of the doping atmosphere from the vessel.

57. **(withdrawn)** A method of manufacturing an optical waveguide preform, said method comprising:

- providing a first drying atmosphere to a soot preform contained in a vessel;

- holding the first drying atmosphere in the vessel for a first reacting time sufficient to at least partially dry the soot preform;

- at least partially refilling the vessel with a second drying atmosphere; and

- holding the second drying atmosphere in the vessel for a second reacting time sufficient to further dry the soot preform.

58. **(withdrawn)** The method of Claim 57 further including, following said step of holding the second drying atmosphere:

- at least partially refilling the vessel with a third drying atmosphere; and
- holding the third drying atmosphere in the vessel for a third reacting time sufficient to further dry the soot preform.

59. **(withdrawn)** The method of Claim 57 including:

- pressurizing the first drying atmosphere about the soot preform during the first reacting time;

- depressurizing the first drying atmosphere about the soot preform at the end of the first reacting time; and

- pressurizing the second drying atmosphere about the soot preform during the second reacting time.

60. **(withdrawn)** The method of Claim 57 including increasing the pressure of at least one of the first drying atmosphere during the first reacting time or the second drying atmosphere during the second reacting time.

61. **(withdrawn)** The method of Claim 60 wherein the vessel is substantially completely gas-sealed throughout said step of increasing the pressure.

62. **(withdrawn)** The method of Claim 57 wherein:
each of the first and second drying atmospheres includes a drying gas;
from the beginning of the first reacting time to the end of the second reacting time, the total pressure of the atmosphere in vessel is maintained substantially constant and the partial pressure of the drying gas is varied.

63. **(withdrawn)** The method of Claim 62 wherein an inert gas is added to the atmosphere in the vessel during and between said steps of holding the first drying atmosphere and holding the second drying atmosphere to compensate for reductions in the partial pressure of the drying gas resulting from diffusion of the drying gas into the soot preform.

64. **(withdrawn)** The method of Claim 62 wherein the drying gas is added to the atmosphere in the vessel during at least one of the first and second reacting times to compensate for reductions in the partial pressure of the drying gas resulting from diffusion of the drying gas into the soot preform.

65. **(withdrawn)** The method of Claim 62 further including the step of purging the drying atmosphere from the vessel prior to said step of refilling the vessel with the second drying atmosphere.

66. **(withdrawn)** The method of Claim 57 wherein:
each of the first and second drying atmospheres includes a drying gas;
and
the drying gas is added to the atmosphere in the vessel during at least one of the first and second reacting times to compensate for reductions in the partial pressure of the drying gas resulting from diffusion of the drying gas into the soot preform.

67. **(withdrawn)** The method of Claim 57 including pressurizing an outer surface of the vessel to offset pressurization within the vessel.

68. **(withdrawn)** The method of Claim 57 including supporting a reinforcing sleeve about the vessel during at least the first and second reacting times.

69. **(withdrawn)** The method of Claim 57 including rotating the soot preform relative to the vessel.

70. **(withdrawn)** The method of Claim 57 including sintering the soot preform following the second reacting time.

71. **(withdrawn)** The method of Claim 70 wherein the soot preform remains in the pressure chamber throughout each of the steps recited in Claims 1 and 70.

72. **(withdrawn)** The method of Claim 57 including:
 pressurizing the first drying atmosphere to a gage pressure of at least 0.1 atm gageduring the first reacting time; and
 pressurizing the second drying atmosphere to a gage pressure of at least 0.1 atm gageduring the second reacting time.

73. **(withdrawn)** The method of Claim 57 including:
 pressurizing the first drying atmosphere to a first pressure during the first reacting time; and
 pressurizing the second drying atmosphere to a second pressure during the second reacting time;
 wherein the second pressure is different than the first pressure.

74. **(withdrawn)** The method of Claim 57 including increasing a total pressure of the drying atmosphere in the vessel during the reacting time.

75. **(withdrawn)** The method of Claim 57 wherein the first reacting time is between about 1 and 60 minutes.

76. **(withdrawn)** The method of Claim 57 wherein the second reacting time is between about 5 and 30 minutes.

77. **(withdrawn)** The method of Claim 57 wherein the second reacting time is longer than the first reacting time.

78. **(withdrawn)** The method of Claim 57 including:
heating the first drying atmosphere to a temperature of between about 300 and 1200 °C during the first reacting time; and
heating the second drying atmosphere to a temperature of between about 300 and 1200 °C during the second reacting time.

79. **(withdrawn)** The method of Claim 57 including:
heating the first drying atmosphere to a first temperature during the first reacting time; and
heating the second drying atmosphere to a second temperature during the second reacting time;
wherein the second temperature is different from the first temperature.

80. **(withdrawn)** The method of Claim 57 wherein the first drying atmosphere is simultaneously maintained in a quartz muffle and at a temperature less than 1200 C during the first reacting time.

81. **(withdrawn)** The method of Claim 57 wherein each of the first and second drying atmospheres includes a halogen-containing compound.

82. **(withdrawn)** The method of Claim 81 wherein the first and second halogen-containing compounds are the same.

83. **(withdrawn)** The method of Claim 81 wherein the first and second drying atmospheres each include a halogen-containing compound selected from the group consisting of Cl_2 , SiCl_4 , GeCl_4 , SOCl_2 , or POCl_3 .

84. **(withdrawn)** The method of Claim 57 wherein the first and second drying atmospheres each include an inert gas selected from the group consisting of He, Ar, Ne, and N_2 .

85. **(withdrawn)** A method of manufacturing an optical waveguide preform, said method comprising:

- providing a drying atmosphere to a soot preform contained in a vessel;
- holding the drying atmosphere in the vessel for a reacting time of between about 1 and 60 minutes to at least partially dry the soot preform; and
- evacuating at least a portion of the drying atmosphere from the vessel at the end of the reacting time.

86. **(withdrawn)** The method of Claim 85 including:

- at least partially refilling the vessel with a second drying atmosphere following the reacting time; and
- holding the second drying atmosphere in the vessel for a second reacting time sufficient to further dry the soot preform.

87. **(withdrawn)** The method of Claim 85 including:

- pressurizing the drying atmosphere about the soot preform for the reacting time; and
- depressurizing the drying atmosphere about the soot preform at the end of the reacting time.

88. **(withdrawn)** The method of Claim 87 wherein the vessel is substantially completely gas-sealed throughout said step of pressurizing the drying atmosphere.

89. **(withdrawn)** The method of Claim 87 further including, following said step of depressurizing the drying atmosphere:

replacing at least a portion of the drying atmosphere with a second drying atmosphere about the soot preform; and

pressurizing the second drying atmosphere about the soot preform for a second reacting time of no more than 30 minutes to further dry the soot preform.

90. **(withdrawn)** The method of Claim 89 wherein said step of pressurizing the second drying atmosphere includes pressurizing the second drying atmosphere to a gage pressure of at least 0.1 atm gage.

91. **(withdrawn)** The method of Claim 90 wherein said step of pressurizing the second drying atmosphere includes pressurizing the second drying atmosphere to a gage pressure of at least 0.5 atm gage.

92. **(withdrawn)** The method of Claim 89 wherein the second reacting time is between about 5 and 30 minutes.

93. **(withdrawn)** The method of Claim 89 wherein said step of pressurizing the second drying atmosphere includes heating the second drying atmosphere to a temperature of between about 850 and 1100 °C.

94. **(withdrawn)** The method of Claim 85 including pressurizing an outer surface of the vessel to offset pressurization within the vessel.

95. **(withdrawn)** The method of Claim 85 including rotating the soot preform relative to the vessel.

96. **(withdrawn)** The method of Claim 85 including sintering the soot preform following the reacting time.

97. **(withdrawn)** The method of Claim 85 including pressurizing and heating the drying atmosphere about the soot preform to a gage pressure of at least 0.1 atm and a temperature of less than 1200 °C.

98. **(withdrawn)** The method of Claim 85 including pressurizing the drying atmosphere to a gage pressure of at least 0.1 atm.

99. **(withdrawn)** The method of Claim 98 including pressurizing the drying atmosphere to a gage pressure of at least 0.5 atm.

100. **(withdrawn)** The method of Claim 85 wherein the reacting time is between about 5 and 30 minutes.

101. **(withdrawn)** The method of Claim 85 including heating the drying atmosphere to a temperature of between about 850 and 1100 °C.

102. **(withdrawn)** The method of Claim 85 wherein the drying atmosphere includes a halogen-containing compound selected from the group consisting of Cl₂, SiCl₄, GeCl₄, SOCl₂, or POC_l₃.

103. **(withdrawn)** A method of manufacturing an optical waveguide preform, said method comprising:

 flowing a pulse of a process gas into a vessel to form a drying atmosphere in the vessel about a soot preform, the process gas including a drying gas;

 maintaining the soot preform in contact with the drying atmosphere for a reacting time sufficient to at least partially dry the soot preform; and

 evacuating at least a portion of the drying atmosphere from the vessel at the end of the reacting time.

104. **(withdrawn)** The method of claim 103 wherein the drying atmosphere is maintained at ambient pressure about the soot preform during the reacting time.

105. **(withdrawn)** he method of claim 103 wherein the drying atmosphere is pressurized about the soot preform to a drying pressure greater than ambient pressure during the reacting time.

106. **(withdrawn)** The method of claim 103 including flowing a second pulse of the process gas into the vessel to form a second drying atmosphere in the vessel about a soot preform following said step of evacuating at least a portion of the drying atmosphere from the vessel.

107. **(withdrawn)** An apparatus for manufacturing an optical waveguide preform using a soot preform, said apparatus comprising:

- a pressure vessel defining a pressure chamber adapted to contain the soot preform;

- a supply of process gas including at least one of a doping gas and a drying gas;

- a fluid control system including:

- a flow control device operable to prevent and allow flow of said process gas into and out of said pressure chamber to form an atmosphere about the soot preform; and

- a pressurizing device operable to pressurize said atmosphere in said pressure chamber;

- a process controller operative to control said flow control device and said pressurizing device to:

- pressurize said atmosphere about the soot preform to a selected pressure for a reacting time of between about 1 and 30 minutes to dope or dry the soot preform; and

- depressurize said atmosphere about the soot preform at the end of said reacting time; and

- a heater operable to heat said atmosphere and the preform in said pressure chamber.

108. **(withdrawn)** The apparatus of Claim 107 wherein said process controller is operative to pressurize said atmosphere about the soot preform to a gage pressure of at least 0.1 atm gage.

109. **(withdrawn)** The apparatus of Claim 107 wherein said process gas includes a halogen-containing compound.

110. **(withdrawn)** The apparatus of Claim 109 wherein said process gas includes a halogen-containing compound selected from the group consisting of Cl_2 , GeCl_4 , SiCl_4 , SiF_4 , SF_6 , CF_4 , C_2F_6 , COF_2 , $\text{C}_2\text{F}_2\text{Cl}_2$, and F_2 .

111. **(withdrawn)** The apparatus of Claim 107 wherein said process gas includes a fluorine-containing compound.

112. **(withdrawn)** The apparatus of Claim 111 wherein said process gas includes a fluorine-containing compound selected from the group consisting of SiF_4 , SF_6 , CF_4 , C_2F_6 , COF_2 , $\text{C}_2\text{F}_2\text{Cl}_2$, and F_2 .

113. **(withdrawn)** The apparatus of Claim 112 wherein said process gas includes a fluorine-containing compound selected from the group consisting of SiF_4 , SF_6 , and CF_4 .

114. **(withdrawn)** The apparatus of Claim 107 wherein said process gas supply includes a mixture of said at least one of a dopant gas and a drying gas and an inert gas.

115. **(withdrawn)** The apparatus of Claim 107 including a supply of inert gas and wherein said fluid control system is operable to prevent and allow flow of said inert gas into and out of said pressure chamber to form a portion of said atmosphere about the soot preform.

116. **(withdrawn)** The apparatus of Claim 107 wherein said flow control device includes at least one valve.

117. **(withdrawn)** The apparatus of Claim 116 wherein said at least one valve includes a mass flow controller.

118. **(withdrawn)** The apparatus of Claim 107 wherein said pressurizing device includes at least one of:

- a compressor; and
- a pressurized tank and a regulator.

119. **(withdrawn)** The apparatus of Claim 107 including a holding assembly operative to hold and rotate the soot preform in said pressure chamber.

120. **(withdrawn)** The apparatus of Claim 119 wherein said holding assembly includes a holder adapted to directly engage and support the soot preform and a drive unit non-mechanically coupled to said holder and operable to rotate said holder relative to said chamber.

121. **(withdrawn)** The apparatus of Claim 120 wherein said drive unit is magnetically coupled to said holder.

122. **(withdrawn)** The apparatus of Claim 107 including a reinforcing sleeve surrounding at least a portion of said pressure vessel.

123. **(withdrawn)** The apparatus of Claim 122 wherein said reinforcing sleeve is formed of a material selected from the group consisting of silicon carbide, silicon nitride, graphite, and alumina.

124. **(withdrawn)** The apparatus of Claim 107 including a second pressure vessel surrounding at least a portion of said first pressure vessel, said first and second pressure vessels defining a second pressure chamber therebetween.

125. **(withdrawn)** The apparatus of Claim 107 wherein said wherein substantially all of the portions of said pressure vessel interfacing with said pressure chamber are formed of quartz.

126. **(withdrawn)** The apparatus of Claim 107 including a second heater.

127. **(withdrawn)** The apparatus of Claim 107 wherein said heater is a variable temperature heater.

128. **(withdrawn)** An apparatus for manufacturing an optical waveguide preform using a soot preform and an atmosphere, said apparatus comprising:

- a) a first pressure vessel having inner and outer opposed surfaces, said inner surface defining a first pressure chamber adapted to contain the soot preform and the atmosphere;
- b) a second pressure vessel surrounding at least a portion of said first pressure vessel, said first and second pressure vessels defining a second pressure chamber therebetween; and
- c) a pressurizing system operable to pressurize each of the first and second pressure chambers to control a differential between pressures on said inner and outer surfaces of said first pressure vessel.

129. **(withdrawn)** The apparatus of Claim 128 wherein substantially all of said inner surface of said first pressure vessel that interfaces with said first pressure chamber is formed of quartz.

130. **(withdrawn)** The apparatus of Claim 128 wherein said pressurizing system includes a compressor operable to pressurize said first chamber.

131. **(withdrawn)** The apparatus of Claim 128 adapted to allow said first pressure vessel to be pressurized to a gage pressure of at least 0.5 atm and heated to a temperature of at least 1000 °C without displacing said inner surface more than 20%.

132. **(currently amended)** A method of manufacturing an optical waveguide preform, said method comprising:

providing a soot preform contained in a vessel;

adding a quantity of a first doping gas to the vessel to provide a first doping atmosphere to the soot preform, the first doping gas being selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂;

holding the soot preform in contact with the first doping atmosphere within the vessel, and maintaining the first doping atmosphere between 1100 and 1300 °C, for a first reacting time sufficient to at least partially dope the soot preform, wherein the first doping atmosphere is pressurized to a first doping pressure greater than ambient pressure, and wherein no more than 0.5 slpm of the first doping atmosphere flows out of the chamber during the first reacting time;

adding a quantity of a second doping gas to the vessel to provide a second doping atmosphere to the soot preform, the second doping gas being selected from the group consisting of SiF₄, SF₆, CF₄, C₂F₆, COF₂, C₂F₂Cl₂, and F₂; and

holding the soot preform in contact with the second doping atmosphere within the vessel, and maintaining the second doping atmosphere between 1100 and 1300 °C, for a second reacting time sufficient to at least partially dope the soot preform, wherein the second doping atmosphere is pressurized to a second doping pressure greater than ambient pressure, and wherein no more than 0.5 slpm of the second doping atmosphere flows out of the chamber during the second reacting time.

133. **(previously presented)** The method of claim 132 wherein the vessel is sealed gas-tight throughout the first reacting time.

134. **(previously presented)** The method of claim 133 wherein the vessel is sealed gas-tight throughout the second reacting time.

135. **(previously presented)** The method of claim 132 wherein at least a portion of the first doping atmosphere is evacuated from the vessel at the end of the first reacting time.

136. **(previously presented)** The method of claim 132 wherein at least a portion of the second doping atmosphere is evacuated from the vessel at the end of the second reacting time.

137. **(previously presented)** The method of claim 132 wherein no more than 0.1 slpm of the first doping atmosphere flows out of the chamber during the first reacting time.

138. **(previously presented)** The method of claim 132 wherein no more than 0.1 slpm of the second doping atmosphere flows out of the chamber during the second reacting time.